

UNCLASSIFIED

AD 271 457

*Reproduced
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

CATALOGED BY ASTIA

AS AD NO. 271 457

271 457

Rock Island Arsenal Laboratory



TECHNICAL REPORT

CONVERSION COATING FOR CHROMIUM

By

R. H. Wolff

Department of the Army Project No. 593-32-006

Ordnance Management Structure Code No. 5010.11.810

Report No. 61-4360

Copy No.

IEL 1-9-100-9

Date 4 December 1961

DISTRIBUTED BY THE
OFFICE OF TECHNICAL SERVICES
U. S. DEPARTMENT OF COMMERCE
WASHINGTON 25, D. C.


THIS REPORT MAY BE DESTROYED WHEN
NO LONGER REQUIRED FOR REFERENCE

Report No. 61-4360


Copy No. _____

CONVERSION COATING FOR CHROMIUM

By


R. H. Wolff

Approved by:


A. C. HANSON
Laboratory Director

4 December 1961

Department of the Army Project
No. 593-32-006
Ordnance Management Structure Code
No. 5010.11.810

Rock Island Arsenal
Rock Island, Illinois

ASTIA Availability Notice:

Qualified requesters may obtain
copies of this report from ASTIA.

ABSTRACT

Selected chemicals in water solution were used electrolytically in an effort to produce an oxide conversion coating upon electrodeposited chromium. It was found that some materials and solution combinations are capable of producing thin, colored, iridescent films at the anode or cathode and sometimes at both electrodes. Chromic oxide films were obtained in what appears to be the hydrous form at the anode. Such films could be produced as relatively thick gels. Unfortunately, these gels have no bond to the basis chromium and upon removal from solution, dry to a loosely adherent powder. No satisfactory method was found for producing chromic oxide supplementary coatings on chromium surfaces using aqueous solution techniques.

RECOMMENDATIONS

It is recommended that no further work be considered for production of an oxide conversion coating on chromium by aqueous solution methods. However, it is believed that further investigation for the production of a colored oxide coating be considered from another direction. Such direction might include the use of molten salts with the resultant disadvantages of higher operating temperatures. It is also possible that an alloy is needed with the chromium to provide a matrix for bonding the oxide.

CONVERSION COATING FOR CHROMIUM

CONTENTS

	<u>Page No.</u>
Object	1
Introduction	1
Procedure and Results	3
Discussion	10
Literature References	13
Distribution	14

CONVERSION COATING FOR CHROMIUM

OBJECT

To develop a conversion coating on chromium that will provide the advantages of chromium in hardness and abrasion resistance, coupled with the camouflage appearance and corrosion resistance of chromium oxide. To accomplish this conversion of chromium by electrolytic action using chemicals in water solution.

INTRODUCTION

Layers of chromium metal are used extensively in Ordnance where hardness, wear and heat resistance are required. In normal application the chromium is electrodeposited. The resulting deposits are usually bright and the surfaces are not particularly receptive to the retention of paint. Black chromium may be used in certain cases but because of the structure of the coating, many of the normal properties of bright chromium are not retained. Consequently, the uses of chromium for external coatings are limited where camouflage measures are a consideration.

It has been observed that heating stainless steel in the air sometimes causes the surface to become discolored. This discolored layer varies from green to black and has been found to be very resistant to cleaning operations. The oxide is most readily removed by high current electropolishing or by abrasive buffing, either of which results in stripping some of the basis material from the surface.

As a coating for external use, this oxide film offers advantages in that it forms a dull nonreflective surface in a natural camouflage color range. The surface by visual observation is smooth but not glossy so that a possibility of good paint bonding exists.

The stainless steels derive their remarkable resistance to corrosion from the presence of chromium. The effectiveness of the chromium in establishing passivity is shown by the increased resistance to oxidizing conditions as the chromium content is increased(1).

It is believed by many investigators that passivation results from the presence of a thin oxide or hydrate film on the metal, stabilized by chromium. The rate at which steels develop passivity depends upon the chromium content. Steels that contain more than approximately 20% chromium become

passive in the atmosphere without developing even a slight film of rust. Since the chromium plays such an important part in this corrosion mechanism, it would appear that a conversion surface coating of chromium based on relatively pure chromium oxide, would result in an effective corrosion barrier, and also provide characteristics different from those associated with chromium plate alone.

Available data show that there are three oxides of chromium: the monoxide or chromous oxide, CrO ; the sesquioxide or chromic oxide, Cr_2O_3 ; and the trioxide or chromic acid anhydride, CrO_3 . The monoxide is not very stable. It is a black pyrophoric powder which can be made to burst into flames if struck sharply or if heated in the air⁽²⁾. It is most readily prepared from a chromium amalgam by oxidation, either with nitric acid or in the air.

Chromium trioxide is a dark red crystalline compound which is usually prepared commercially in flakes. It is also called chromic anhydride or chromic acid. The latter term, which is commonly used, is incorrect by chemical terminology. CrO_3 is very hygroscopic, readily soluble in water and melts with some decomposition, at a temperature of 387°F (197°C).

Chromic oxide is a compound most widely used and recognized as a green pigment. The melting point has been given as 4415°F (2435°C). It is a semiconductor. The color varies from light green in finely divided particles to almost black in large crystals. The color turns from green to brown when heated but is restored to green upon cooling. In crystalline form, Cr_2O_3 is as hard as corundum or next to diamond in hardness on the Moh scale. Chromic oxide is produced by heating finely divided chromium in the air or by igniting various salts such as hydrous chromic oxide, ammonium or mercurous chromate. The result is finely divided powder, the fineness of which depends upon the temperature of ignition. Chromic oxide is insoluble in water, alcohol or acetone and only slightly soluble in all acids and alkalis except hot 70% perchloric acid which changes it to CrO_3 .

X-ray diffraction examination was made of a typical grey-green coating, formed by heating a stainless steel strip to approximately 1000°F in an uncontrolled atmosphere. It was established that the coating was primarily chromic oxide Cr_2O_3 with the presence of CrO and a possible complex including iron, $(\text{CrFe})_2\text{O}_3$.

There are a number of references in the literature reporting analyses of similar films to be Cr_2O_3 and mixtures of spinel. These films were produced at various temperatures

from 932°F (500°C) to 2192°F (1200°C) (3,4). In general the experiments were conducted in controlled atmospheres of oxygen. Other data relating to the composition of the oxide films were gathered from investigations to determine the oxidation resistance of highly alloyed chromium steels heated to high temperatures for extended time periods (5,6). The conditions of high temperature and oxygen atmosphere readily produce the oxide coatings.

To make practical use of an oxide coating, one approach would be to heat the object in an oven or furnace at suitable temperature and atmosphere to produce the oxide layer. The disadvantage would be restriction of the process by size of the oven. Furthermore, it is not metallurgically feasible to subject steels to the relatively high temperatures required without danger of changing the properties by heat treatment effects. On the other hand, if chromium plating is considered as a prerequisite, it would be relatively easy to duplicate the chromium tank in size and use a solution to process objects of any size that could be plated.

Much data has been assembled concerning the chromium oxides resulting from study of appropriate ferrous-chromium alloys for high temperature uses. Very little work has been done to explore the possibility of anodically forming the oxide after the manner of anodizing of metals such as aluminum. Johansen, et al (7) in an experiment regarding anodic oxidation at very low current densities, used an ammonium borate solution. This experiment, conducted under constant conditions, examined aluminum, chromium, hafnium, niobium, tantalum, vanadium and zirconium. Chromium was among the metals which did not result in forming a film under this set of conditions.

The efforts of the present work were directed toward the development of an oxide protective coating by electrolytic conversion of chromium metal in aqueous solution.

PROCEDURE AND RESULTS

Test specimens were prepared by plating 10 to 15 mils of chromium on small bars of FS 1018 steel. In size the specimens were 3/16" x 3/8" x 8". The chromium plating was accomplished from a 33 oz./gal. bath with chromium to sulfate ratio of 100 to 1. In test these specimens were used at both electrodes so that observations could be made of the chromium behavior as cathode as well as anode. Unless otherwise noted, solution volumes were made to 300 cc., a quantity adequate for test and not wasteful of chemicals.

Electrode spacings were allowed to vary from 2 to 2-1/2 inches apart and only two electrodes were used, one cathode

and one anode fixed in position so the specimens could not rotate. By this arrangement it was possible to observe the ability of the film to cover the complete specimen. No special pretreatment was given the chromium specimens except to insure they were kept clean between the plating and actual use in test.

The general procedure after immersion and electrical connection of the specimens, involved slowly increasing the voltage until gas bubbles began to form on the cathode. At this point (usually 1.8 volts) the system was observed for several minutes for evidence of attack or coating. The voltage was then increased to determine whether the reactions would change in a visible manner other than acceleration of rate. If no changes were observed up to 9 volts the test specimens were removed from the solution for rinsing in distilled water and examination upon drying. After the experimental work had been started an additional current source was made available so that approximately 24 volts DC could be applied. However, none of the tests showed this increase in potential to be of any particular benefit.

Experimental solutions were used, which on the basis of present knowledge, form coatings on some metals or because of the chemistry involved could produce the conditions for forming the oxide. The solutions are grouped and listed below according to observations of specimens as (1) dissolving action, (2) no visible appearance change, (3) thin colored films, and (4) gel films.

The first two groups are based upon action in the solution. The resulting action was positive attack on the specimen with usually an orange colored film originating at the surface of the specimen and quickly coloring the whole solution. This film was very dense at the specimen surface and appeared to roll down along the specimen and slowly disperse into the solution. The film is so completely soluble that all the color stayed in the solution and upon lifting the specimen from the test the surface was rinsed clean as it was drawn from the liquid. Specimens from this group showed etching of the chromium in relatively short time.

Group 2 specimens were probably undergoing dissolving attack also, but at a slow rate so that the specimens were not different in appearance after the experiment. Coloring of the solution was masked by the initial color resulting from solution composition.

Dissolving Action

<u>Solution</u>	(300 cc volume unless otherwise noted)	<u>Comment</u>
Nitric Acid	(10 cc) 75°F	
Oxalic Acid	5% 75°F	
Sodium Chloride	5% 75°F	
Nickel Nitrate	5% 140°F	Cathode etched slightly
Sodium hypophosphite	10% 75°, 120°, 180°	
Sodium hydroxide	10% 180°, 6 volts	
Zinc phosphatizing solution	160° 12 volts	Cathode turns black, smutty, rubs off
Sodium perborate	5% 160° up to 18 volts	
Sodium peroxide	5% 160°	
Zinc silicofluoride	5% 75° 3-4 volts	Cathode coated with zinc
Copper sulfate	5% 75° 2 volts	Cathode coats with non- adherent copper
Chromic acid	10% 75° 10 volts	Cathode iridescent golden brown
Potassium thiosulfate	5% 75° 3-1/2 volts 150° 6 volts	Soluble green film at anode
Sodium sulfite	5% 75° 6 volts 150° 6 volts	Green anode film which strips as soluble when specimen is moved or re- moved from sol ⁿ

Dissolving Action

<u>Solution</u>	<u>Comment</u>
Sodium aluminate 10 gm Sodium silicate 10 gm 130°F 2-6 volts	Anode: yellow dissolving film
+ Sodium dihydrogen phosphate 6 gm 130° 2 volts	Anode reaction same as above
Chromium fluoride 2 gms 75°F 10 volts	Anode: dissolving yellow film
Cobaltous chloride 4 gms 75°F 4 volts	

No Appearance Change In Specimens

(Dissolving action assumed.)

<u>Solution</u>	<u>Comment</u>
Chromic acid (pH 0.2) 10%	
Chromic acid (pH* 3.8) 10%	Anode <u>very</u> faint yellow
Chromic acid (pH* 6.8) 10%	
Chromic acid (pH* 9.8) 10%	
Chromic acid 10% Ammonium hydroxide (5cc) Sodium hydrosulfite 5 gms	Exothermic reaction heats to 150° and solution turned to gel. Current flows but no coatings produced.
Chromic acid 5% Sodium hydrosulfite 2 gms	Upon addition of 5 gms more hydrosulfite the sol ⁿ gelled

Thin, Colored Films

Chromic acid 10% (pH* 4.3) 140° 2.2 volts	Anode: blue with bubble spots Cathode: uniform blue violet
Chromic acid (pH* 3.8) 10% 140°	Anode: faint yellow
Chromic acid (pH* 3.8) 10% 180° 2.2 volts	Anode: yellow Cathode: dark yellow w/ blue patch center
Chromic acid (pH* 3.8) 10% (a) 180° 1.9 volts (b) 180° 2.2 volts (c) fresh spec. at room temperature 1.8 volts (d) temperature raised to 180°	Cathode test only: Blue iridescent Uniform yellow No change Yellow color

*pH adjustments made by adding ammonium hydroxide.

Thin, Colored Films

<u>Solution</u>	<u>Comment</u>
Sodium hydrosulfite 10% 180° 4-6 volts	Anode: etched olive drab colored coating Cathode: black smut wipes off
10% Chromic acid heats as used at 6 volts	Anode: black Cathode: brown iridescent
Potassium permanganate (1 gm) 75° 6 volts	Anode: faint olive drab film Cathode: hvy. purple film easily scratched

Gel Films Formed

Sodium hydroxide 5% (400 cc) Sodium hydrosulfite 5 gms 150° 3 to 6 volts	Anode: green film
Sodium hydroxide 5% (300 cc) Sodium hydrosulfite 5 gms 150° 4-1/2	Anode: brilliant green
Sodium sulfide 5% Sodium hypophosphite 5% 75° 3 volts	Anode: dull green
Sodium sulfide 1 gm 75° 6 volts Add approx. 2 gms more sulfide	Anode: Dull blue grey Green gel film
Sodium hydrosulfite 10 gms Sodium hydroxide 2 gms 75° 2-6 volts	Anode: green gel poor adhesion in sol ⁿ
Sodium sulfhydrate 10 gms 75° 6 volts	Anode: green film quickly turns orange
Sodium hydroxide (5 gm) Sodium sulfide (5 gm) 75° 2-6 volts	Anode: dissolving yellow film becomes gel film of ugly orange & green color

Gel rinses away in running water
leaving faint blue iridescence.

Gel Films Formed

<u>Solution</u>	<u>Comment</u>
Sodium aluminate (12 gm) 150° 2-6 volts	Anode: orange film with scattered more intense colored dots. Film comes loose w/ gentle rubbing under stream of H ₂ O.
Same as above w/ Sodium fluoride (5 gms)	Anode reaction same as above.

DISCUSSION

The coatings of oxide that form on metals during oxidation differ widely in their ability to inhibit further oxidation. Such oxides can generally be divided into three main types: (1) those in which the coating has essentially no protective effect and in which the coating grows linearly with respect to time, (2) those that have a limited protective effect in that the rate of oxide growth decreases with time, and (3) those in which the coating completely protects the metal after it has grown to a definite thickness. It has been suggested that in the first type the oxide is porous. This would be the case, for example, if the volume of oxide formed from a volume of metal is less than the volume of metal. If the reverse is true, i.e., the ratio of oxide volume to metal volume is greater than unity, the oxide forms an intermediate or completely protective coating⁽⁸⁾.

In addition to this relationship of oxide coating to metal, consideration must be given to the circumstance of oxide formation. Subjecting a metal to the conditions of anodizing in any particular electrolyte produces the following possibilities:

(a) The anode reaction products may be soluble in the electrolyte. In this case the metal is dissolved until the solution is saturated or the metal is gone.

(b) The reaction products may be almost insoluble in the electrolyte and form a strongly adherent and nonconducting film on the anode. The film growth continues until the resistance of the film prevents the current from reaching the anode (basis metal). Films formed in this manner are usually thin.

(c) The reaction products may be sparingly soluble in the electrolyte and form a strongly adherent film which is nonconducting when dry over the anode.

(d) The reaction products may be sparingly soluble and form a nonadherent film. If a suitable electrolyte of high concentration is used, electropolishing may be possible.

In relating the experimental results to these defining conditions, it may be determined that chromium produces an oxide coating in which the oxide volume produced from a volume of metal is greater than unity⁽⁹⁾. A comparison of several commonly used metals over which the ratio of oxide volume to metal volume is more than one, may be made as follows⁽⁹⁾:

<u>Metal</u>	<u>Ratio</u>	<u>Oxide volume</u> <u>Metal volume</u>
Aluminum		1.38
Chromium		1.97
Copper		1.71
Nickel		1.64
Zinc		1.44

From these indications a satisfactory protective oxide coating is expected to form with chromium. A consideration of the experimental electrolytic results, however, places the solution method of oxide production into the type indicated by (a) or (d). By reference to results under dissolving reactions, the chromium anode reaction products were soluble in solutions of strong inorganic acids or bases; with solutions of salts of a strong acid or a strong base; and with strong organic acid such as oxalic acid. In the case of the gel forming reactions, the chromium anode products were found to be sparingly soluble. The films were moderately adherent while wet but could be easily brushed away when dried. Increasing the voltage on these specimens resulted in growth phenomena that clearly indicated the film did not prevent the current passage to the basis metal. These films correspond closely to the hydrous oxide, $\text{Cr}_2\text{O}_3 \cdot x\text{H}_2\text{O}$. This gel is slightly soluble in acid solution when first formed but becomes insoluble upon aging or heating⁽¹⁰⁾. Aging is also accelerated in alkaline solution. Treatments of this sort were used in unsuccessful efforts to prevent the oxide from separating from the basis chromium. Specimens on which the green gel was produced were variously processed by soaking in ammonium hydroxide and drying in the air or by use of an oven (forced convection) or a muffle furnace. Baking temperatures were varied from 150°F (65°C) to 600°F (312°C). In all of these cases the result was a fine green powder with no bond to the basis chromium.

It was found that a range of colors could be produced by variation of voltage to the cathode in chromic acid solutions of pH approximately 3.6. The influence of voltage could be seen in the color effects caused by current density. These effects were such that a specimen might be golden yellow around the edges and have an iridescent blue center spot which changed in size with variation of the voltage (and current density). These films offered varying and usually slight

resistance to abrasion and moderate resistance to attack by concentrated hydrochloric acid. The coatings appeared to be very thin and did not show evidence of becoming thicker with time. It is speculated that the colors were due to optical interference effects. It is known that similar thin films can be produced from chromate solutions upon mild steel cathodes(11).

Films such as these offer slight potential use as a superficial color layer or as a base for paint. The ease with which the color is changed with current density would present a problem in the production of uniform appearance. This problem arises from the fact that irregular variation of current density normally results from the shape and size of the work piece. Present benefits of such a thin, colored coating are not considered sufficiently rewarding in return for the additional operation.

Failure to produce a heavy chromium oxide layer in a fashion similar to the anodizing of aluminum to aluminum oxide is disappointing. The possibility does exist that only thin layers of protective chromium oxide are obtainable. This situation could occur if the bond is strong between the chromium and chromium oxide and weak or nonexistent between the growth of chromium oxide layers formed over the initial oxide layer.

LITERATURE REFERENCES

1. ASM Metals Handbook, p. 557 (1948).
2. Udy, Marvin J., Chromium, Vol. 1, p. 113, Reinhold Publishing Corp., New York, (1956).
3. E. A. Gulbransen, W. R. McMillan, Ind. & Eng. Chem., 45 1734, (1953).
4. E. A. Gulbransen, K. F. Andrew, Jour. Electrochem. Soc. 106 941, (1959).
5. E. A. Gulbransen, K. F. Andrew, Jour. Electrochem. Soc. 106 249, (1959).
6. E. J. Felten, Jour. Electrochem. Soc. 108 490, (1961).
7. H. A. Johansen, G. B. Adams, Jr., P. Van Rysselberghe, Jour. Electrochem. Soc. 104 339, (1957).
8. H. H. Uhlig, Corrosion Handbook, p. 11, John Wiley & Sons, London 1948.
9. F. Seitz, Physics of Metals, p. 189 McGraw-Hill Book Co., New York 1943.
10. M. J. Udy, Chromium, Vol. 1, p. 120 Reinhold Pub. Corp., New York 1956.
11. Corrosion Prevention and Control, Vol. 7, No. 9, p. 32, London 1960.

DISTRIBUTION

	<u>No. of Copies</u>
Chief of Ordnance Dept. of the Army Washington 25, D. C. ATTN: ORDTB-Materials	1
Commanding General Ordnance Weapons Command Rock Island, Illinois ATTN: ORDOW-TX	1
ORDOW-IX	1
ORDOW-FM	1
Commanding General Ordnance Ammunition Command Joliet, Illinois ATTN: ORDLY-QTPC	1
Commanding General Ordnance Tank Automotive Command Detroit Arsenal Center Line, Michigan ATTN: ORDMC-RS	1
Commanding General U.S. Army Ordnance Special Weapons Ammunition Command Dover, New Jersey	1
Commanding General Army Ballistic Missile Agency U.S. Army Ordnance Missile Command Redstone Arsenal, Alabama ATTN: ORDAB-RR	1
Commanding General U.S. Army Rocket & Guided Missile Agency Redstone Arsenal, Alabama ATTN: Mr. R. L. Wetherington, ORDXR-OCP	5
Director Ordnance Materials Research Office Watertown Arsenal Watertown 72, Mass. ATTN: PS&C Division	1

DISTRIBUTION

	<u>No. of Copies</u>
Commanding Officer U. S. Army Research Office (Durham) Box CM, Duke Station Durham, North Carolina	1
Commanding General Aberdeen Proving Ground, Maryland ATTN: Coating & Chemical Laboratory	2
Technical Library, ORDBG-LM, Bldg. 313	2
Commanding General Frankford Arsenal Philadelphia 37, Pa. ATTN: ORDBA-1300	1
Commanding Officer Frankford Arsenal Library Branch, 0270, Bldg. 40 Bridge & Tacony Streets Philadelphia 37, Pa.	1
Commanding Officer Picatinny Arsenal Dover, New Jersey ATTN: Plastics & Packaging Laboratory	1
PLASTEC	1
Commanding Officer Raritan Arsenal Metuchen, New Jersey ATTN: ORDJR-OML	1
Commanding Officer Raritan Arsenal Metuchen, New Jersey ATTN: H&K Lab. Division, ORDJR-E	1
Commanding Officer Springfield Armory Springfield 1, Mass. ATTN: ORDBD-TX	1
Commanding Officer Watertown Arsenal Watertown 72, Mass. ATTN: Technical Information Section	1

DISTRIBUTION

	<u>No. of Copies</u>
Commanding Officer Watervliet Arsenal Watervliet, New York ATTN: ORDBF-RR	1
Commanding Officer Army Chemical Center Army Environmental Health Laboratory Army Chemical Center, Maryland	1
Commanding Officer Anniston Ordnance Depot Anniston, Alabama ATTN: Chemical Laboratory	1
Ordnance Officer Headquarters U. S. Army Caribbean Fort Clayton, Canal Zone	1
Commanding Officer Diamond Ordnance Fuze Laboratories Connecticut Avenue & Van Ness Street, N.W. Washington 25, D. C. ATTN: Technical Reference Section	1
Department of the Navy Bureau of Ordnance Washington 25, D. C. ATTN: Code Re 1	2
Commander (Code 5557) U.S. Naval Ordnance Test Station China Lake, California	1
Commander Armed Services Technical Information Agency Arlington Hall Station Arlington 12, Virginia ATTN: TIPDR	10
Prevention of Deterioration Center National Academy of Science National Research Council 2101 Constitution Avenue Washington 25, D. C.	1

DISTRIBUTION

No. of Copies

Commanding General
Ordnance Weapons Command
Rock Island, Illinois
ATTN: ORDOW-TX
for
release to

3

Commander
British Army Staff
ATTN: Reports Officer
3100 Massachusetts Avenue, N. W.
Washington 8, D. C.

Commanding General
Ordnance Weapons Command
Rock Island, Illinois
ATTN: ORDOW-TX
for
release to

3

Canadian Army Staff, Washington
2450 Massachusetts Avenue, N. W.
Washington 8, D. C.
ATTN: GSO-1, A & R Section

Army Reactor Branch
Division of Reactor Development
Atomic Energy Commission
Washington 25, D. C.

1

Dr. W. R. Lucas
George C. Marshall Space Flight Center
M-S & M-M
Huntsville, Alabama

1

National Aeronautics and Space
Administration
Marshall Space Flight Center
Huntsville, Alabama
ATTN: Mr. Wm. A. Wilson, M-F & AE-M,
Bldg. 4712

1

Office of Technical Services
U. S. Department of Commerce
Main Building, Room 6814A
Washington 25, D. C.
ATTN: Acquisitions Branch,
(Mr. George K. Taylor, Chief)

100

AD Accession No.
Rock Island Arsenal Laboratory, Rock Island,
Illinois
CHROMIUM COATING FOR CIRCULAR
BY R. E. DAVIS

RIA Lab. Rep. 61-4369, 4 Dec 61, 17 p. incl.
films. (ables, (RA Project No. 603-33-406,
and Code No. 6018.11.612) Confidential
report.

Selected chemicals in water solution were used electrolytically in an effort to produce an oxide conversion coating upon electro-deposited chromium. It was found that some materials and solution combinations are capable of producing thin, colored, iridescent films at the anode or cathode and sometimes at both electrodes. Chromium oxide films were obtained in what appears to be the hydrogen form at the anode. Such films could be produced on relatively thick galls. Unfortunately, these galls have to be used to the (Cont.) over

AD Accession No.
Rock Island Arsenal Laboratory, Rock Island,
Illinois
CHROMIUM COATING FOR CIRCULAR
BY R. E. DAVIS

RIA Lab. Rep. 61-4369, 4 Dec 61, 17 p. incl.
films. (ables, (RA Project No. 603-33-406,
and Code No. 6018.11.612) Confidential
report.

Selected chemicals in water solution were used electrolytically in an effort to produce an oxide conversion coating upon electro-deposited chromium. It was found that some materials and solution combinations are capable of producing thin, colored, iridescent films at the anode or cathode and sometimes at both electrodes. Chromium oxide films were obtained in what appears to be the hydrogen form at the anode. Such films could be produced on relatively thick galls. Unfortunately, these galls have to be used to the (Cont.) over

UNCLASSIFIED

1. Anodes-Coatings
2. Chromium Compounds-Applications
3. Chromium Coatings
4. Chromium Plating-Coatings
5. Metal Coatings-Production Materials
6. Metal Film-Coatings

DISSEMINATION:
Copies obtainable
from 68714-002

AD Accession No.
Rock Island Arsenal Laboratory, Rock Island,
Illinois
CHROMIUM COATING FOR CIRCULAR
BY R. E. DAVIS

RIA Lab. Rep. 61-4369, 4 Dec 61, 17 p. incl.
films. (ables, (RA Project No. 603-33-406,
and Code No. 6018.11.612) Confidential
report.

Selected chemicals in water solution were used electrolytically in an effort to produce an oxide conversion coating upon electro-deposited chromium. It was found that some materials and solution combinations are capable of producing thin, colored, iridescent films at the anode or cathode and sometimes at both electrodes. Chromium oxide films were obtained in what appears to be the hydrogen form at the anode. Such films could be produced on relatively thick galls. Unfortunately, these galls have to be used to the (Cont.) over

AD Accession No.
Rock Island Arsenal Laboratory, Rock Island,
Illinois
CHROMIUM COATING FOR CIRCULAR
BY R. E. DAVIS

RIA Lab. Rep. 61-4369, 4 Dec 61, 17 p. incl.
films. (ables, (RA Project No. 603-33-406,
and Code No. 6018.11.612) Confidential
report.

Selected chemicals in water solution were used electrolytically in an effort to produce an oxide conversion coating upon electro-deposited chromium. It was found that some materials and solution combinations are capable of producing thin, colored, iridescent films at the anode or cathode and sometimes at both electrodes. Chromium oxide films were obtained in what appears to be the hydrogen form at the anode. Such films could be produced on relatively thick galls. Unfortunately, these galls have to be used to the (Cont.) over

UNCLASSIFIED

1. Anodes-Coatings
2. Chromium Compounds-Applications
3. Chromium Coatings
4. Chromium Plating-Coatings
5. Metal Coatings-Production Materials
6. Metal Film-Coatings

DISSEMINATION:
Copies obtainable
from 68714-002

UNCLASSIFIED

1. Anodes-Coatings
2. Chromium Compounds-Applications
3. Chromium Coatings
4. Chromium Plating-Coatings
5. Metal Coatings-Production Materials
6. Metal Film-Coatings

DISSEMINATION:
Copies obtainable
from 68714-002

basis chromium and upon removal from solution, dry to a loosely adherent powder. No satisfactory method was found for producing chromic oxide supplementary coatings on chromium surfaces using aqueous solution techniques.

basis chromium and upon removal from solution, dry to a loosely adherent powder. No satisfactory method was found for producing chromic oxide supplementary coatings on chromium surfaces using aqueous solution techniques.

basis chromium and upon removal from solution, dry to a loosely adherent powder. No satisfactory method was found for producing chromic oxide supplementary coatings on chromium surfaces using aqueous solution techniques.

basis chromium and upon removal from solution, dry to a loosely adherent powder. No satisfactory method was found for producing chromic oxide supplementary coatings on chromium surfaces using aqueous solution techniques.